

xlaFORM

Material Properties

Tensile Strength PSI	4,350
Compressive Strength PSI	22,818
Flexural Strength	7,257
Notched Izod Impact Ft./Lb	.58
Elongation	0.3
Shore D Hardness	95
Heat Deflection Temperature	280 C